

## REMARKS

In view of the above amendments and following remarks, reconsideration and further examination are requested.

Replacement formal drawings for Figures 8 and 9 have been provided so as to designate these figures --Prior Art--.

The specification and abstract have been reviewed and revised to make editorial changes thereto and generally improve the form thereof, and a substitute specification and abstract are provided. No new matter has been added by the substitute specification and abstract.

Claims 23-40 have been canceled, and claims 41-57 have been added. The currently pending claims are free of the informalities as noted by the Examiner in section (2) of the Office Action. With regard to these claims, claims 42-49 correspond to the first embodiment of removing a molded disk as described on page 17, line 16 through page 23, line 10 of the original specification. Claims 50-57 correspond to the second embodiment of removing a molded disk as described on page 27, line 18 through page 29, line 23 of the original specification. And, claim 41 is believed to be generic for each of these embodiments.

Claims 36 and 37 were rejected under 35 U.S.C. § 103(a) as being unpatentable over Asai in view of JP '211, and further in view of Moynagh, Maus et al. or Sakaida et al. This rejection is respectfully traversed for the following reasons.

Initially, the courtesies extended by Examiner Lorengo during the personal interview conducted on October 19, 2004, are greatly appreciated. During this interview, the invention was discussed along with the claims and the rejection of record. Specifically, Applicants' undersigned representative explained the significance of opening the molds by at most 0.3 mm so as to separate a molded optical disk from the stamper. Examiner Lorengo explained why opening the molds by this distance would have been obvious in view of the teachings of JP '221, such that the rejection of record would be maintained.

Examiner Lorengo did express, however, that reciting a step-wise opening of the molds, with the maximum opening distance being 0.3 mm, appeared to differentiate the invention over the prior art of record. Accordingly, without acquiescing to the appropriateness of the prior art rejection, and

solely to further advance prosecution of this application, new claim 41 has been drafted taking this suggestion into account.

Specifically, claim 41 requires a step-wise opening of the molds, as well as limiting the total distance moved by the molds during this step-wise opening to be about 0.3 mm. Please note that this claim slightly differs from that discussed during the interview by not reciting that the distance moved by the molds is at most 0.3 mm, because from a further review of the specification it appears to be clear that the maximum distance moved by the molds during the step-wise opening is more than 0.3 mm.

In this regard, with regard to the first embodiment, as explained beginning in the initial paragraph on page 18 of the original specification, the molds 104, 109 are first moved apart by approximately  $20\mu\text{m}$  such that a second release space part 176 is formed. Then, gas is supplied to this release space part 176 so as to separate molded disk 16 from mold 104. Then, as explained beginning in the final paragraph beginning on page 21 of the original specification, the molds are **further moved** by a distance of at most 0.3 mm such that a first release space part 175 is formed. Then, gas is supplied to this release space part 175 so as to separate molded disk 16 from stamper 115. Thus, the maximum total distance moved by the molds during the step-wise separation thereof is slightly greater than 0.3 mm, i.e.  $20\mu\text{m} + 0.3\text{ mm}$ . Description of the second embodiment as expressed on page 27, line 18 through page 29, line 23 of the original specification, also supports this movement of the molds to be greater than 0.3 mm.


None of the references relied upon teach or suggest the step-wise separation as now recited in claim 41, whereby claims 41-57 are allowable over these references either taken alone or in combination.

In view of the above, it is respectfully submitted that the application is now in condition for allowance, and an early Notice of Allowance is earnestly solicited.

If after reviewing this Amendment, the Examiner believes that any issues remain which must be resolved before the application can be passed to issue, the Examiner is invited to contact the Applicants' undersigned representative by telephone to resolve such issues.

Respectfully submitted,

Takaaki HIGASHIDA et al.

By:   
\_\_\_\_\_  
Joseph M. Gorski  
Registration No. 46,500  
Attorney for Applicants

JMG/edg  
Washington, D.C. 20006-1021  
Telephone (202) 721-8200  
Facsimile (202) 721-8250  
November 5, 2004



## DESCRIPTION

### OPTICAL DISK MOLDING APPARATUS AND METHOD

This application is a Nation Stage application of PCT/JP00/01455, filed March 10, 2000.

#### 5 TECHNICAL FIELD

[0001] The present invention relates to an optical disk molding apparatus for molding and ~~taking-out~~ removing optical disks such as, for example, CDs (compact disks), LDs (laser disks) and the like, and a method for molding optical disks ~~carried-out~~ performed by the optical disk molding apparatus.

10

#### BACKGROUND ART

[0002] A molding apparatus 1 having a structure as shown in Fig. 8 has been conventionally used for forming molded objects corresponding to, for instance, ~~the~~ CDs, LDs and the like optical disks. The molding apparatus 1 of ~~the~~ this type is roughly comprised of a  
15 nozzle 2 for injecting a plasticized molten resin ~~plasticized~~ to form ~~the~~ molded objects, a fixed mold 4, and a movable mold 9. A cavity 12 ~~to-into~~ which the molten resin is injected to mold ~~the~~ molded an object is formed between the fixed mold 4 and the movable mold 9.

[0003] The fixed mold 4 has a sprue bush 6 fitted thereto. The sprue bush 6 includes a recess part 13 ~~to-into~~ which the nozzle 2 can ~~come-in~~ be inserted and ~~out~~ removed, and a sprue  
20 part 7 for communicating with the recess part 13 and the cavity 12. The sprue bush 6 is positioned relative to the fixed mold 4 by being fitted ~~in-at~~ at an inner circumferential face 5a of a locating ring 5 set to a fixed plate 3. The sprue part 7 is designed to be concentric with the locating ring 5 and the nozzle 2 when the sprue bush 6 is fitted in the locating ring 5.

[0004] Meanwhile, the movable mold 9 has a stamper 15 which is installed facing the  
25 cavity 12 and ~~to-on~~ on which data to be transferred to the molded object are formed.

[0005] In the molding apparatus 1, for injecting the plasticized molten resin ~~to-into~~ into the cavity 12, the nozzle 2 moves down and comes into contact with a contact face 6b of a bottom part 6a of the sprue bush 6, whereby an injection hole 2a of the nozzle 2 communicates with the sprue part 7. The plasticized molten resin is injected from the nozzle 2 by a plunger (or screw) .  
30 ~~The-This~~ injected molten resin is injected via the sprue part 7 of the sprue bush 6 into the cavity 12. Pits and projections constituting the ~~above~~ data of the stamper 15 are thus transferred to the

molded object.

[0006] For releasing the molded object from the movable mold 9, simultaneously with when a mold opening operation is performed by driving the movable mold 9 after the resin is injected, ~~the~~ air is blown to the molded object from a path 10 formed ~~to~~ in the movable mold 9. Ejection ~~to~~ of the sprue part 7 and the molded object is ~~carried out~~ performed after the movable mold 9 is completely opened, with the air being simultaneously blown to the molded object from the ~~above~~ path 10, thereby separating the molded object from the movable mold 9. The molded object is transferred to outside of the molding apparatus by a take-out apparatus after ~~the~~ this separation is finished.

[0007] The conventional molding apparatus 1 ~~in~~ of the above structure has problems as follows. Specifically, the stamper 15 and the molded object relatively tightly adhere ~~by~~ to one another because of the molding operation performed for ~~the~~ creating a molded object. As indicated in the right half of the movable mold 9 in Fig. 8, the stamper 15 is held to the movable mold 9 in a manner so that an inner circumferential part 15a and an outer circumferential part 15b of the stamper are caught by the movable mold 9. After ~~the~~ a mold opening operation is performed after ~~the~~ molding, as shown in Fig. 9, an ejector pin 11 projects from the movable mold 9, whereby the molded optical disk 16 is pushed up towards the fixed mold 4, and the optical disk 16 and the stamper 15 are separated from each other.

[0008] In ~~the~~ an event that a middle part, between the inner circumferential part 15a and the outer circumferential part 15b in a diametrical direction of the stamper 15, is not released from the molded object 16 when the mold opening operation is performed, the stamper 15 is deformed so as to float ~~the~~ away from a central part ~~from~~ of the movable mold 9 as indicated in the drawing. The larger an angle  $\theta$  1 between a data transferred face 17 of the molded object 16, to which the data of the stamper 15 are to be transferred, and a data forming face 18 of the stamper 15, having ~~the~~ pits and projections corresponding to the data ~~is~~, the ~~larger~~ the more projection parts of the data forming face 18 rub side faces of projecting parts formed ~~to~~ on the data transferred face 17, thereby deforming the data transferred face 17. There is a problem in that ~~the~~ data cannot be correctly formed ~~to~~ on the molded object 16 in consequence of ~~the~~ this deformation, resulting in quality deterioration of the molded object in some cases. More specifically, ~~the~~ deformation of the data transferred face 17 appears as a whitish phenomenon or ~~the~~ a so-called jitter in a ROM (read only memory) when the ROM is constituted of the optical

disk, and data is written exceeding an allowable range in a RAM (random access memory) when the RAM is constituted of the optical disk.

[0009] In the stamper 15, as described above, since the projection parts of the data forming face 18 are rubbed and worn, frequent replacement of ~~the extremely expensive stamper stampers~~ 15 becomes necessary to eliminate the above problem of the molded object and to maintain ~~the~~ quality of the molded object, which leads to an increase of costs.

[0010] The present invention is devised to solve the above problems and has for its object to provide an optical disk molding apparatus and method which can prevent deterioration in quality of molded objects.

### **DISCLOSURE SUMMARY OF INVENTION**

[0011] In order to achieve the aforementioned objective, an optical disk molding apparatus is ~~provided~~ according to a first aspect of the present invention ~~which has~~ comprises a pair of molds to open and clamp, ~~wherein in which~~ a stamper having data to be transferred to an optical disk to be molded ~~with~~ via the molds is provided at a cavity ~~in defined between~~ the molds, ~~and~~. The apparatus molds the optical disk in the cavity, and ~~opens~~ the molds are opened after molding the optical disk. The apparatus is characterized by comprising:

a mold moving device having an electric motor for ~~the~~ opening of the molds; and

a gas supply device for supplying a gas to a release space part formed by releasing part of the molded optical disk from one of the mold molds by ~~the~~ opening ~~by of the molds by the~~ mold moving device so as to totally separate ~~totally~~ the optical disk and the ~~mold~~ one of the molds from each other ~~with~~ via a pressure of the gas.

[0012] According to the optical disk molding apparatus of the first aspect, the molds are opened by the electric motor of the mold moving device and therefore can be opened by a minute ~~move~~ movement amount in comparison with ~~the~~ related art. The ~~move~~ movement amount can be controlled more easily than in the related art. In other words, it becomes possible to supply the gas by the gas supply device to the release space part at ~~the time~~ a point in time when the ~~move~~ movement amount in which the release space part is formed by the mold opening is attained. The gas is supplied to the release space part formed by the ~~move~~ movement amount highly accurately controlled as compared with the related art, thereby peeling the optical disk from the ~~mold~~ one of the molds. A quality deterioration at least at one of a data transferred face and a data non-form

face of the molded optical disk can be prevented accordingly.

[0013] The release space part may have a first release space part formed by releasing part of the optical disk from the stamper, and the gas supply device may have a first gas supply device for supplying the gas to the first release space part so as to totally separate ~~totally~~ the optical disk and the stamper from each other ~~with the~~ via pressure of the gas. The apparatus may further comprise a controller for controlling to drive the mold moving device and the first gas supply device, which ~~makes-causes~~ the mold moving device to open the molds to separate the stamper and the optical disk, with a ~~move-movement~~ distance not damaging a data transferred face of the optical disk, from a mold clamp state in which the optical disk is molded so as to form the first release space part, and ~~makes-causes~~ the first gas supply device to work to supply the gas to the first release space part at a point in time ~~point~~ when the first release space part is formed.

[0014] By having the first gas supply device and the controller as above, the molds are opened by the ~~move-movement~~ distance, not damaging the data transferred face of the optical disk, from the mold clamp state in which the optical disk is molded, thereby forming the first release space part, and the gas is supplied to the first release space part when the first release space part is formed, so that the optical disk and the stamper are wholly separated from each other. No damage is therefore brought about to the data transferred face of the optical disk at the ~~time~~ point in time when the first release space part is formed. Moreover, the optical disk and the stamper are separated from each other ~~by~~ via the gas pressure after the first release space part is formed. Data is accordingly prevented, ~~all over the~~ an entirety of the data transferred face of the optical disk, from being damaged, and the quality deterioration of the optical disk as a molded body can be prevented.

[0015] The ~~move-movement~~ distance ~~with~~ by which the controller makes the mold moving device open the molds may be a mold open amount of 0.3mm, or smaller, exceeding the mold clamp state.

[0016] The first release space part is formed to peel the optical disk by opening the molds by the above ~~move-movement~~ ~~amount~~ distance, whereby the quality deterioration of the optical disk can be prevented.

[0017] The controller can make the gas supply device supply the gas with a pressure of  $24.5 \times 10^4$  Pa or larger.

[0018] ~~The quality~~Quality deterioration of the optical disk can be prevented by the performing a releasing operation ~~through the~~ via gas supply at the pressure.

[0019] An optical disk molding apparatus according to a second aspect of the present invention can be configured so that in the optical disk molding apparatus of the first aspect, the release space part has a second release space part formed by releasing part of a data non-form face, opposite to a data transferred face of the molded optical disk, from the other one of the molds ~~mold by the opening of the molds~~ by the mold moving device, and

the gas supply device has a second gas supply device for supplying ~~the gas to the second~~ release space part so as to totally ~~separate totally~~ the data non-form face and the ~~mold~~ other one of the molds from each other ~~with the~~ via pressure of the gas.

[0020] According to the optical disk molding apparatus of the second aspect as above, because of installing the second gas supply device for supplying the gas to the second release space part, the data non-form face of the optical disk can be released from the ~~mold~~ other of the molds while the data non-form face is prevented from being deteriorated in quality.

[0021] In the optical disk molding apparatus of the above second aspect, the apparatus may be designed so that the molds have a movable mold movable by the mold moving device along a thickness direction of the optical disk to be molded, and a fixed mold arranged opposite to the movable mold,

the stamper is fitted to the movable mold, and

the controller further makes the mold moving device move the movable mold from ~~the a~~ mold clamp state ~~with by a move~~ movement amount by which the second release space part is formed, and which is smaller than a ~~move~~ movement amount for forming a first release space part by releasing part of the optical disk from the stamper, and makes the second gas supply device work to supply ~~the gas to the second release space part at the time~~ a point in time when the second release space part is formed.

[0022] Since the controller also controls ~~the operation of the mold moving device and the~~ second gas supply device, the data transferred face and the data non-form face of the optical disk can be released from the molds while ~~the quality deterioration is prevented for the~~ these two faces.

[0023] According to an optical disk molding method of a third aspect of the present invention, the method comprises molding an optical disk, and opening a pair of molds after



molding the disk; the molds being opened and clamped, and ~~having defining~~ a cavity, with a stamper ~~which is provided~~ at the cavity and which has data to be transferred to the optical disk to be molded ~~with by~~ the molds. The method is characterized by comprising:

opening the molds so as to separate the stamper and the optical disk from a mold clamp state in which the optical disk is molded, ~~by with a move-movement~~ distance of 0.3mm, or smaller, exceeding the mold clamp state ~~and so as not damaging to damage~~ a data transferred face of the optical disk; and

supplying a gas to a first release space part at a ~~time-point~~ in time when the first release space part is formed between part of the optical disk and the stamper by releasing the optical disk from the stamper by ~~the~~ opening of the molds, and then totally separating ~~totally~~ the optical disk and the stamper from each other.

[0024] The above optical disk molding method of the third aspect may be designed so that the method further comprises:

forming a second release space part by releasing part of a data non-form face, opposite to the data transferred face of the molded optical disk, from one of the mold-molds due to the opening of the molds before forming the first release space part;

totally separating ~~totally~~ the data non-form face and the ~~mold~~ one of the molds from each other by supplying a gas ~~to~~ into the second release space part at a ~~time-point~~ in time when the second release space part is formed; and

forming the first release space part after ~~the~~ total separation of the data non-form face and the ~~mold~~ one of the molds from each other, thereby totally separating the optical disk and the stamper from each other.

## BRIEF DESCRIPTION OF THE DRAWINGS

[0025] These and other objects and features of the present invention will become clear from the following description taken in conjunction with the preferred embodiments thereof with reference to the accompanying drawings in which:

[0026] Fig. 1 schematically shows ~~the~~ a constitution of an optical disk molding apparatus according to a first embodiment of the present invention;

[0027] Fig. 2 is a sectional view of the optical disk molding apparatus of Fig. 1 in a state with a first release space part formed;

[0028] Fig. 3 is a flow chart of operations of an optical disk molding method ~~in~~ performed by the optical disk molding apparatus of Fig. 1;

[0029] Fig. 4 is a diagram of results of experiments ~~carried out~~ performed to obtain a ~~move-movement~~ distance of a movable mold and a supply gas pressure, whereby quality deterioration of optical disks is prevented ~~in~~ during operation of the optical disk molding apparatus of Fig. 1;

[0030] Fig. 5 schematically shows ~~the~~ a constitution of an optical disk molding apparatus according to a second embodiment of the present invention;

[0031] Fig. 6 is a diagram of a modification of the first embodiment and the second embodiment;

[0032] Fig. 7 is a diagram explanatory of a mold opening operation ~~in~~ of the optical disk molding apparatus of the first embodiment;

[0033] Fig. 8 is a diagram showing ~~the~~ a constitution of a conventional optical disk molding apparatus; and

[0034] Fig. 9 is a diagram of a state in which an optical disk is released in the conventional optical disk molding apparatus of Fig. 8.

## ~~BEST MODE FOR CARRYING OUT THE INVENTION~~ DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0035] An optical disk molding apparatus, and an optical disk molding method which are embodiments of the present invention will be described below with reference to the drawings. It is to be noted here that like parts are designated by like reference numerals throughout the drawings. The optical disk molding method is ~~carried out~~ performed by the optical disk molding apparatus.

### FIRST EMBODIMENT

[0036] Fig. 1 schematically shows ~~the~~ a constitution of an optical disk molding apparatus 101 according to a first embodiment. As is shown in ~~the~~ this drawing, although the optical disk molding apparatus 101 is fundamentally constructed in a similar manner to the above-described conventional optical disk molding apparatus 1, the optical disk molding apparatus 101 is characterized in that a gas supply system is installed also to a fixed mold, a moving device for

moving a movable mold is improved, and a controller 161 for controlling operations of each part constituting the apparatus to ~~carry out the~~ perform an optical disk molding method to be detailed later is installed. The apparatus will be described in detail hereinbelow.

[0037] The optical disk molding apparatus 101 is constituted as follows. Specifically, the optical disk molding apparatus 101 is roughly comprised of a nozzle 102 for injecting a plasticized molten resin ~~plasticized~~ to mold optical disks as molded objects, a fixed mold 104, and a movable mold 109. A cavity 112 ~~to~~ into which the molten resin is injected, thereby molding ~~the~~ a molded object, is formed between the fixed mold 104 and the movable mold 109. The nozzle 102 has an injection unit 131 installed thereto. The injection unit 131 includes a plunger or a screw, and an arrangement necessary for injecting the plasticized molten resin. To the nozzle 102 is connected a nozzle moving device 132 so that the nozzle 102 is movable back and forth to a recess part 113, to be described below, along a thickness direction of ~~the~~ an optical disk molded in the cavity 112. The above injection unit 131 and the nozzle moving device 132 are connected to ~~a~~ the controller 161 and controlled to ~~drive~~ be driven by the controller 161.

[0038] A sprue bush 106 having the recess part 113, to which the nozzle 102 can move back and forth, and a sprue part 107 for communicating the recess part 113 with the cavity 112, is attached to the fixed mold 104. The sprue bush 106 is positioned to the fixed mold 104 by being fitted to an inner circumferential face 105a of a locating ring 105 set to a fixed plate 103. The sprue part 107 is adapted to be concentric with the locating ring 105 and the nozzle 102 when the sprue bush 106 is fitted into the locating ring 105.

[0039] Further, the fixed mold 104 has a second gas passage 151 formed ~~thereto with the~~ therewith via utilization of a gap between the fixed mold and the sprue bush 106, and a gap part between the fixed mold and the fixed plate 103. One end of the second gas passage 151 is connected to a second gas supply device 152 installed outside the fixed mold 104, and ~~the other~~ another end of the second gas passage is opened to the cavity 112 circumferentially along ~~the~~ a periphery of the sprue bush 106. The second gas supply device 152, which is connected to the controller 161 supplies, as will be discussed in detail later, ~~the~~ air according to ~~the~~ this embodiment through the second gas passage 151 to a gap part between a mirror face 1041 of the fixed mold 104 and part of the optical disk so as to separate the mirror face 1041 and the optical disk from each other after the optical disk is molded. The mirror face 1041 is a flat face for forming a data non-form face 177 of the optical disk to be molded.

[0040] A stamper 115, ~~on~~ to which data to be transferred to the optical disk is formed, is provided at the movable mold 109 to face the cavity 112. Similar to the stamper 15 described earlier, the stamper 115 is held to the movable mold 109 with an inner circumferential part 115a and an outer circumferential part 115b being caught by the movable mold 109. A mold moving device 136 for moving the movable mold 109 in the thickness direction of the optical disk molded in the cavity 112 is connected to the movable mold 109 for ~~the~~ a purpose of ~~the~~ a so-called mold opening operation and mold clamping operation. According to the present embodiment as will be described later, since it is necessary to move the movable mold 109 by a several tenths of a millimeter or a several micrometers ~~order~~ in during starting the a mold opening operation, a toggle mechanism 1362 including an AC servo motor 1361 of an electric motor, as a driving source, and a ball screw ~~is~~ are adopted for the mold moving device 136 in the embodiment. The movable mold 109 is moved by rotating the ball screw about an axis of the ball screw by the AC servo motor 1361. The movable mold 109 can hence be moved with an accuracy of a 1 $\mu$ m level by ~~the~~ adoption of ~~the~~ this electric motor type toggle mechanism 1362.

[0041] A cylindrical cutter 117 is installed ~~to~~ in the movable mold 109 correspondingly to a central part of the optical disk to be molded so as to form a through hole ~~to~~ in the ~~center~~ central part of the optical disk after ~~the~~ molding thereof. The cylindrical cutter 117 is moved by a cutter driving device 135 along the thickness direction of the optical disk. The movable mold 109 also has a first gas passage 110 cylindrically formed corresponding to the central part of the optical disk and inside the cylindrical cutter 117. A first gas supply device 134 is connected to the first gas passage 110 for supplying ~~the~~ air in ~~the~~ this embodiment to the first gas passage 110. As will be detailed later, the first gas supply device 134 supplies the air through the first gas passage 110 to a gap part between the stamper 115 and the optical disk to separate the stamper 115 and the optical disk after the optical disk is molded.

[0042] A cylindrical ejector pin 111 is installed ~~to~~ in the movable mold 109, which ejector pin relatively moves in the a thickness direction ~~to~~ of the movable mold 109, thereby projecting ~~to~~ from or being stored ~~into~~ in the movable mold 109 when the movable mold 109 moves in the thickness direction.

[0043] The above mold moving device 136, the cutter driving device 135, and the first gas supply device 134 are connected to the controller 161 and controlled to ~~drive~~ be driven by the controller 161.

[0044] The optical disk molding apparatus 101 further includes an optical disk take-out device 141 for ~~taking out~~ removing from within the fixed mold 104 and the movable mold 109 the optical disk, molded and peeled subsequent to ~~the a~~ mold opening operation of the movable mold 109, by the mold driving device 136. The optical disk take-out device 141 is connected to the controller 161 so as to be controlled in operation by the controller 161.

[0045] Operation of the optical disk molding apparatus 101 of the present embodiment constituted as above will be ~~depicted~~ described below. Since operation in relation to molding the optical disk in the cavity 112 is not different from ~~the a~~ conventional molding operation described before, ~~the~~ description thereof will be omitted here. Characteristic operation ~~in of~~ the apparatus of this embodiment ~~of with regard to~~ the mold opening operation, and ~~the~~ releasing of the molded optical disk from the stamper 115 after molding the optical disk, will be mainly described below.

[0046] As shown in Fig. 3, after the optical disk is molded, the controller 161 drives the mold driving device 136 ~~in during~~ a step (designated by "S" in the drawing) S1 to move the movable mold 109 in a direction of ~~the a~~ mold opening operation, which is the thickness direction of the molded optical disk 16. A ~~move~~ movement velocity of the movable mold 109 at this time is a first ~~move~~ movement velocity to be described later, i.e., 2-3mm/sec. The controller 161 drives the second gas supply device 152 at a ~~time~~ point in time when the movable mold moves in the mold opening direction by approximately 20μm in ~~the this~~ embodiment from a mold clamp state in which the optical disk is molded, thereby supplying ~~the~~ air through the second gas passage 151. In other words, as a result of the above movement by approximately 20μm, a second release space part 176 is generated between part of the data nonform face 177 of the molded optical disk 16 and the mirror face 1041 of the fixed mold 104. The data non-form face 177 is exaggeratively illustrated for the sake of description in Fig. 7.

[0047] Next ~~in a~~ during step S2, the gas is supplied to the second release space part 176 at a point in time ~~point~~ when the second release space part 176 is formed. The data non-form face 177 and the mirror face 1041 are entirely separated from each other ~~all over with~~ via a pressure of ~~the gas in a~~ supplied during step S3.

[0048] According to the present embodiment, ~~the~~ air supply from the second gas supply device 152 is ~~carried out~~ performed with an air pressure of  $39.2 \times 10^4$  Pa for 0.1 second. The above approximately 20μm, indicative of a timing for starting ~~the~~ air supply, is a value set on the

a basis of the fact that a thickness tolerance of the optical disk 16 to be molded is  $\pm 10\mu\text{m}$ . However, the value should be appropriately set in accordance with a change of an optical disk molding condition, etc and the like. ~~The~~ A reason for supplying the gas to the second release space part 176 when the second release space part 176 is generated, thereby totally separating the data non-form face 177 ~~and from~~ the mirror face 1041 is as described below.

[0049] If the data non-form face 177 and the mirror face 1041 are separated dependently on the mold opening operation without supplying the gas from the second gas supply device 152, ~~the~~ this separation advances from ~~the~~ a central part towards an outer circumferential part of the optical disk 16 and therefore, the outer circumferential part adheres to the mirror face 1041 until ~~the~~ an end of the separation. In consequence, a time while the molded optical disk 16 is kept in contact with the mold varies in a diametrical direction thereof during ~~the~~ a separation process, ~~bringing about thereby causing~~ a temperature difference ~~to of~~ the optical disk 16 in the diametrical direction. As a result, the outer circumferential part of the optical disk 16 is not made ~~transparently to be transparent~~, but is hazed to raise problems in terms of ~~an~~ appearance and a quality of the optical disk. For preventing ~~the~~ this phenomenon, the above gas supply from the second gas supply device 152 is ~~carried out~~ performed when the second release space part 176 is formed, so that the data non-form face 177 and the mirror face 1041 are separated ~~all from each other~~ at once, thus restricting ~~the~~ a temperature difference to a minimum. The timing of starting the air supply can be considered as a timing whereat an appearance of the haze can be prevented.

[0050] Controlling to start the above gas supply at the ~~time~~ point in time when the movable mold moves by a ~~move~~ movement amount of approximately  $20\mu\text{m}$  is enabled by adopting the toggle mechanism 1362 having the AC servo motor 1361 as the mold driving device 136 as described before, thereby enabling ~~controlling control of~~ a greatly minute ~~move~~ movement amount in comparison with ~~the~~ related art. Since ~~the~~ control of ~~the~~ a minute ~~move~~ movement amount is enabled, ~~the~~ gas supply can be started at the same ~~timing at all times~~ time ~~in during~~ each separation operation for each optical disk, and ~~the~~ quality can be ~~uniformed~~ made to be uniform for ~~in~~ each optical disk.

[0051] The gas supply from the second gas supply device 152 is started at ~~the~~ a point in time ~~point~~ when the mold opening operation is performed to a predetermined position according to the present embodiment as above, and although it is likely to be inferior to the present embodiment in terms of ~~the~~ an effect of ~~uniforming the~~ making quality uniform, ~~an~~ air pressure

may be applied as a modified example to the second gas passage 151 by the second gas supply device 152 before the mold opening operation is performed. The air pressure to be applied is of a level whereby the second release space part 176 is formed when the movable mold moves, e.g., by the above approximately 20 $\mu$ m. The pressure is, for example, 39.2 x 10<sup>4</sup> Pa as mentioned before.

[0052] The phenomenon of ~~the-an~~ appearance of haze is easy to ~~take place~~ result particularly when the stamper 115 is provided at the movable mold 109. The stamper 115 is therefore preferably provided at the fixed mold 104 to avoid ~~the-this~~ problem of ~~the-an~~ appearance of haze as will be discussed later.

[0053] ~~In a~~During step S4, the movable mold 109 is further moved in the mold opening direction to a preset origin position. ~~The move~~ Movement velocity at this time is a second ~~move~~ movement speed to be described later which exceeds the above first ~~move-movement~~ velocity, namely, 200-300mm/sec. The movable mold 109 is opened further ~~from to~~ the origin position by a ~~move-movement~~ distance of 0.3mm or smaller, that is, exceeding 0 and not larger than 0.3mm. As shown in Fig. 2, by performing step S4 of the mold opening operation ~~in the step 4~~, the ejector pin 111 projects from a storage position 171, where the pin is stored in the movable mold 109, by the above ~~move-movement~~ distance 172 out of the movable mold 109. In other words, a value of the illustrated ~~move-movement~~ distance 172 becomes the aforementioned "exceeding 0 and not larger than 0.3mm". The controller 161 sets the ~~move-movement~~ velocity of the movable mold 109 when the second release space part 176 is formed, and the first ~~move-movement~~ velocity when the movable mold is moved by the above ~~move-movement~~ distance 172, to be approximately 1% an output of the AC servo motor of the mold moving device 136, i.e., 2-3mm/sec in the present embodiment.

[0054] When the movable mold 109 is opened by the above ~~move-movement~~ distance 172 "exceeding 0 and not larger than 0.3mm", a first release space part 175 which is a gap of a minute amount is formed ~~to-at~~ the central part of the optical disk 16 between a data transferred face 173 of the optical disk 16 and a data forming face 174 of the stamper 115. Since a size in the thickness direction is smaller in a state when the first release space part 175 is formed, (that is, in a state when the movable mold 109 is opened by the controller 161 by the above move distance 172 of "exceeding 0 and not larger than 0.3mm"), than a gap part formed in the related art, the deformation of the stamper 15 as described with reference to Fig. 9 will not be brought about to

~~the stamper 115~~ result. An angle  $\theta 2$  between the data transferred face 173 of the optical disk 16 and the data forming face 174 of the stamper 115 having pits and projections becomes smaller than ~~the angle~~  $\theta 1$  shown in Fig. 9. The data transferred face 173 is accordingly allowed to slip nearly in the thickness direction of the optical disk from the data forming face 174, so that side  
5 faces of projecting parts formed ~~to-on~~ the data transferred face 173 are prevented from being rubbed and deformed by ~~the-projecting~~ parts of the data forming face 174. Correct data can be formed ~~to-on~~ the optical disk 16 and ~~the-quality deterioration of the optical disk is-~~does not occurred occur.

[0055] ~~The problems~~ Problems of the above haze phenomenon and ~~the-a~~ so-called jitter  
10 when a ROM is formed of the optical disk are solved, and ~~the-a~~ a problem of data being written exceeding an allowable range when a RAM is formed of the optical disk is eliminated.

[0056] Since ~~the-projection~~ parts of the data forming face 174 of the stamper 115 are prevented from being rubbed and deformed, a replacement frequency of the stamper 115 is decreased and costs can be reduced.

15 [0057] The controller 161 drives the first gas supply device 134 ~~in-a~~ during step S5 after performance of the mold opening operation of the movable mold 109 with the above ~~move~~ movement distance 172, thereby supplying ~~the-air~~ to ~~the-formed~~ first release space part 175. At this time, the controller 161 controls ~~the-pressure~~ of the air to be supplied to not smaller than  $24.5 \times 10^4$  Pa.

20 [0058] When the air with ~~the-this~~ thus-controlled pressure is supplied to the first release space part 175, the data transferred face 173 of the optical disk 16 and the data forming face 174 of the stamper 115 are totally separated from each other with ~~the-this~~ air pressure ~~in-a~~ during step S6.

[0059] ~~In-a~~ During step S7, the controller 161 again drives ~~again~~ the mold moving device  
25 136 to move the movable mold 109 in the mold opening direction. The controller 161 moves the movable mold 109 at this time at the second ~~move-movement~~ velocity, greater ~~faster~~ than the first ~~move-movement~~ velocity to finish the opening operation. The second ~~move-movement~~ velocity is approximately 100% ~~the-an~~ output of the AC servo motor of the mold moving device 136, i.e., 200-300mm/sec in ~~the-this~~ embodiment. Since the electric motor type toggle  
30 mechanism is used as the mold moving device 136 in the embodiment as described above, the first ~~move-movement~~ velocity and the second ~~move-movement~~ velocity vary depending on ~~the~~



structure of the mechanism. For instance, the second ~~move-movement~~ velocity can be set to be approximately 350mm/0.4sec.

[0060] ~~In a~~ During step S8, the controller 161 drives the take-out device 141, thereby ~~taking out~~ removing the optical disk 16 from between the fixed mold 104 and the movable mold 109.

[0061] The controller 161 operates the mold moving device 136 thereafter to move the movable mold 109 in a mold clamp direction, and then returns to ~~the a~~ molding operation for optical disks.

[0062] The ~~move-movement~~ distance 172 of "exceeding 0 and not larger than 0.3mm", and the pressure of the air supplied to the first release space part being 175 of  $24.5 \times 10^4$  Pa or larger, are based on grounds as will be described with reference to Fig. 4. In Fig. 4, a circle mark represents ~~nonexistence-non-existence~~ of the deformation at the data transferred face 173 of the optical disk 16 and an "X" mark represents existence of ~~the~~ deformation.

[0063] As is clear from Fig. 4, the data transferred face 173 of the optical disk 16 is not deformed when the pressure of the air to be supplied to the first release space part 175 is not smaller than  $24.5 \times 10^4$  Pa while the ~~move-movement~~ distance 172 is 0.1mm, the data transferred face 173 is not deformed when the pressure of the air to be supplied to the first release space part 175 is not smaller than  $24.5 \times 10^4$  Pa while the ~~move-movement~~ distance 172 is 0.2mm, and the data transferred face 173 is not deformed when the pressure of the air to be supplied to the first release space part 175 is not smaller than  $34.3 \times 10^4$  Pa while the ~~move-movement~~ distance 172 is 0.3mm. In contrast, the data transferred face 173 of the optical disk 16 is deformed ~~regard-less~~ regardless of the pressure of the air supplied ~~air~~ to the first release space part 175 when the ~~move movement~~ distance 172 is 0.5mm.

[0064] Based on the above experimental results, the ~~move-movement~~ distance 172 of "exceeding 0 and not larger than 0.3mm", and the pressure of the air to be supplied to the first release space part being 175 of  $24.5 \times 10^4$  Pa or larger, as described above are obtained. An upper limit of the air pressure is approximately  $49 \times 10^4$  Pa in the present embodiment, which is based on a pressure of ~~the~~ air supplied to a place where the optical disk molding apparatus is seated and which is determined according to a change of ~~the~~ pressure at ~~the~~ this seated place.

[0065] In the above embodiment, it is controlled so that the opening operation of the movable mold 109 is temporarily stopped after ~~the~~ movement of the movable mold 109 ~~in the~~

during step S4 and the air is supplied to the first release space part 175, and thereafter the movable mold 109 is opened in the during step S7 again. However, the control is not limited to this way manner, and the opening operation of the movable mold 109 can be performed continuously from the step S4 to the step S7 without the a temporary stop in the stoppage halfway therebetween.

[0066] The above description ~~related~~ relates to the ~~move~~ movement distance 172 ~~applies~~ applied to the a case where the an optical disk for RAM is molded. On the other hand, in molding the an optical disk for ROM, the ~~move~~ movement distance 172 can be approximately 0.1mm and the gas is supplied with the a pressure of approximately  $19.6 \times 10^4$  Pa for about 0.5-1.0 second. A difference in the ~~move~~ movement distance 172 ~~between~~ corresponding to the RAM and the ROM results from a difference in structure of the these optical disks. That is, the optical disk for RAM has a data record part formed of continuous projection parts and pit parts along the a circumferential direction thereof, and therefore the a gap between the stamper 115 and the optical disk 16, i.e., the above ~~move~~ movement distance 172 should be secured sufficiently large to facilitate flowing the-supplied gas in the diametrical direction of the optical disk 16. On the other hand, since the optical disk for ROM has a data record part formed of discontinuous pit parts, namely, pits formed at intervals along the a circumferential direction, there are gaps arranged towards the an outer circumference. Therefore, the-supplied gas flows in the diametrical direction of the optical disk 16 even if the ~~move~~ movement distance 172 is made smaller than in the case of RAM.

## SECOND EMBODIMENT

[0067] Although the above embodiment adopts a movable stamper system having the stamper 115 provided at the movable mold 109, it is confirmed that the same result can be obtained in a fixed stamper system with the-stamper 115 mounted to the-fixed mold 104.

[0068] More specifically, the-stamper 115 is provided at the-fixed mold 104 in the structure of an optical disk forming apparatus 201 shown in Fig. 5 of a second embodiment. Although the-ejector pin 111, the-cylindrical cutter 117 and the-first gas passage 110 of the movable mold 109 are slightly ~~made~~ different in arrangement from those in the foregoing optical disk forming apparatus 101, the-this difference ~~will~~ does not constitute a specific feature. In the optical disk forming apparatus 201 having the stamper 115 provided at the fixed mold 104,

operation opposite to ~~the operation in~~ of the optical disk forming apparatus 101 is ~~carried out~~ performed regarding ~~the release~~ of the optical disk described with reference to Fig. 3. That is, ~~steps 4-6~~ steps S4-S6 are ~~carried out~~ performed first and ~~steps 1-3~~ steps S1-S3 are ~~carried out~~ performed next. More specifically, the movable mold 109 is moved in ~~the a~~ a mold opening direction ~~with by the move~~ movement distance 172 from the mold clamp state, thereby forming the first release space part 175 ~~to as~~ as a gap between ~~the data forming face 174 of the stamper 115~~ provided at the fixed mold 104 and part of ~~the data transferred face 173 of the optical disk 16,~~ e.g., ~~the a~~ a central part of the optical disk. ~~The air~~ Air is supplied from ~~the second gas supply device 152 to the first release space part 175 similar to the case where the air is supplied from the~~ first gas supply device 134 to the first release space part 175, whereby the data transferred face 173 of the optical disk 16 and the data forming face 174 of the stamper 115 are wholly separated from each other.

[0069] Similar to the case of the optical disk forming apparatus 101 described earlier, side faces of ~~the projection parts formed to on~~ on the data transferred face 173 of the optical disk 16 will not be rubbed and deformed by ~~the projection parts of the data forming face 174 of the stamper 115,~~ so that correct data is formed ~~to on~~ on the optical disk 16, ~~with~~ while generating no quality deterioration of the optical disk. Further, the problems of the above-referred haze phenomenon and the so-called jitter, and the problem of writing data exceeding ~~the an~~ an allowable range, are eliminated. Moreover, costs can be reduced because of a decrease in replacement frequency of the stamper 115.

[0070] ~~The second~~ Second release space part 176 is generated between ~~the data non-form face 177 of the optical disk 16 and part of a mirror face 1091 of the movable mold 109,~~ corresponding to the above mirror face 1041, by moving the movable mold 109 and pushing of ~~the optical disk~~ by the ejector pin 111 through ~~the relative movement.~~ ~~The air~~ Air is supplied from the first gas supply device 134 to the second release space part 176 similar to the case of supplying the air from ~~the second gas supply device 152 to the second release space part 176,~~ thereby entirely separating the data non-form face 177 of the optical disk 16 and the mirror face 1091 of the movable mold 109 ~~all over the faces~~ from each other.

[0071] When the stamper 115 is mounted to the fixed mold 104, as described above, the data transferred face 173 of the optical disk 16 and the data forming face 174 of the stamper 115 are first totally released, and the optical disk 16 is cooled by ~~the such~~ such release. Therefore, ~~the~~

control ~~on the move~~ of a movement amount for generating the second release space part 176 to avoid the above-described appearance of haze is not particularly needed, although it may be executed. Accordingly, in the structure with the stamper 115 provided at the fixed mold 104, an effect of eliminating ~~the a~~ need of the control for preventing ~~the an~~ appearance of haze can be obtained in addition to ~~the an~~ effect of preventing the quality deterioration. When the fixed mold 104 is positioned in a direction opposite to ~~the~~ gravity applied to the movable mold 104 as in the present second embodiment, a further an effect that of dust or the like falling, for example, from the nozzle 102 is hard to ~~affect is obtained~~ realize.

[0072] The optical disk forming apparatus 101 of the first embodiment and the optical disk forming apparatus 201 of the second embodiment described above are so-called cold runner types without having a heating device installed ~~to~~ in a portion of the sprue bush part 106. However, a hot runner type with ~~the such a~~ heating device can be adopted as shown in Fig. 6. Specifically, Fig. 6 shows an optical disk forming apparatus 211 obtained by turning the above optical disk forming apparatus 201 into ~~the a~~ hot runner type. In the optical disk forming apparatus 211, a coil 213 for heating ~~of~~, e.g., an electromagnetic induction type is buried in a sprue bush 212 corresponding to the ~~sprue~~ sprue bush 106, and also a coolant path 215 is formed through which, for example, water is fed to cool the sprue bush 212 if temperature of the sprue bush extraordinarily increases. The heating coil 213 is connected to a power source device 214, and the power source device 214 is controlled in operation by ~~the~~ controller 161. A coolant supply device 216 which at least supplies ~~the~~ coolant, and is controlled in operation by the controller 161, is connected to the coolant path 215. ~~The temperature~~ Temperature of the sprue bush 212 is controlled by controlling operation of the power source device 214 and the coolant supply device 216 by the controller 161.

[0073] In the above first embodiment and second embodiment, ~~the~~ gas is supplied both to the first release space part 175 formed between part of the data transferred face 173 of the optical disk 16 and the data forming face 174 of the stamper 115, and to the second release space part 176 formed between the data non-form face 177 of the optical disk 16 and the mirror face of the mold. However, such an arrangement is possible ~~that the~~ in which gas is supplied to at least one of the spaces, more preferably, ~~the~~ gas is supplied at least to the first release space part 175.

[0074] The entire disclosure of Japanese Patent Application No. 11-66255 filed on March 12, 1999 including the specification, claims, drawings and abstract is incorporated herein by

reference in its entirety.

[0075] Although the present invention has been fully described in connection with the preferred embodiments thereof with reference to the accompanying drawings, it is to be noted that various changes and modifications are apparent to those skilled in the art. Such changes and  
5 modifications are to be understood as included within the scope of the present invention as defined by the appended claims unless they depart therefrom.

10

15

20

25

30

### ABSTRACT OF THE DISCLOSURE

An optical disk molding apparatus and method are provided which prevent data formed ~~to-on~~ a molded object from being damaged and prevent quality deterioration of the molded object. There are provided a mold moving device, a first gas supply device, and a controller, 5 whereby a first release space part is formed by opening molds from a mold clamp state ~~with~~ by a ~~move-movement~~ distance not damaging a data transferred face of the optical disk, and a gas is supplied to the first release space part at a ~~time-point~~ in time when the first release space part is formed, thereby totally separating the optical disk and a stamper from each other. No damage is brought about ~~caused~~ to the ~~a~~ data transferred face at the ~~time-point~~ in time when the first release 10 space part is formed. Since ~~the~~ separation between the optical disk and the stamper is ~~carried out~~ performed via pressure of the gas after the first release space part is formed, data is prevented from being damaged ~~all-over~~ the data transferred face of the optical disk in its entirety.

**AMENDMENTS TO THE DRAWINGS:**

***Replacement Formal Drawings for Figures 8 and 9 have been filed concurrently.***